

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (currently amended) A fibrous web containing a filler, wherein the filler ~~which~~ is a substance in a granular form, having a rotationally symmetrical shape and an inner part and a crust part, whereby the density of the inner part is lower than the crust part, ~~characterized in that~~ wherein
the density of the inner part is about 10 to 90% of that of the crust part, and
the amount of filler used is 3 to 60% of ~~the~~ an amount of solids.
2. (currently amended) A The fibrous web according to Claim 1, ~~characterized in that~~ wherein the density of the inner part of the filler granule is ~~about 10 to 90%, preferably~~ about 40 to 80% of that of the crust part.
3. (previously presented) A The fibrous web according to Claim 1, ~~characterized in that~~ wherein the filler granule consists of pigment particles and a binder.
4. (currently amended) A The fibrous web according to Claim 1, ~~characterized in that~~ wherein the density of the pigment particles is 1500 to 7000 kg/m³, ~~preferably about 2000 to 3100 kg/m³.~~
5. (currently amended) A The fibrous web according to Claim 1, ~~characterized in that~~ wherein the density of the filler granule is 400 to 6300 kg/m³, ~~preferably 600 to 2800 kg/m³,~~ whereby the density of the inner part is about 50 to 5700 kg/m³, ~~preferably 700 to 1500 kg/m³,~~ and the density of the crust part is about 600 to 6300 kg/m³, ~~preferably 1700 to 2000 kg/m³.~~
6. (currently amended) A The fibrous web according to Claim 1, ~~characterized in that~~ wherein the inner part of the filler granule contains rougher pigment particles in relation to the crust part.

7. (currently amended) A The fibrous web according to Claim 1, ~~characterized in that~~ wherein the porosity of the inner part of the filler granule is higher than that of the crust part, whereby the pore volume of the inner part is 10 to 70% by volume, ~~preferably about 30 to 60% by volume.~~

8. (currently amended) A The fibrous web according to Claim 1, ~~characterized in that~~ wherein the crust part of the filler granule comprises metal silicate, metal sulphate or metal carbonate particles, which are bound to one another by means of a cross-linked binder, whereby they form a ~~dense~~ fine and flexible coat that surrounds the inner part.

9. (currently amended) A The fibrous web according to Claim 1, ~~characterized in that~~ wherein the filler particles of the filler granule comprise any inorganic substance, ~~for example, kaolins, ground or precipitated calcium carbonates.~~

10. (currently amended) A The fibrous web according to Claim 1, ~~characterized in that~~ wherein the particle size (ϕ) of the granulated filler is 1 to 100 μm , ~~preferably 5 to 50 μm .~~

11. (currently amended) A The fibrous web according to Claim 1, ~~characterized in that~~ wherein the substance in the granular form is plastically deformable under the effect of pressure and/or temperature.

12. (currently amended) A The fibrous web according to Claim 1, ~~characterized in containing~~ including 3 to 30% by weight of the filler in granular form, whereby the bonding strength of the fibrous web is essentially the same as that of a corresponding fibrous web that contains no filler.

13. (currently amended) A The fibrous web according to Claim 1, ~~characterized in containing~~ including over 30% by weight of the filler in granular form.

14. (Withdrawn, Currently Amended) A method for manufacturing a fibrous web, such as a board, paper or non-woven web containing a filler and having a good tensile strength, the method comprising the inclusion of the filler in the fibrous web, the filler being a substance in a granular form and having a rotationally symmetrical shape and an inner part and a crust part, and the density of the inner part being lower than the crust part, ~~characterized in that~~ wherein the density of the inner part is about 10 to 90% of that of the crust part, and the amount of filler used is 3 to 60% of the amount of solids.

15. (Withdrawn, Currently Amended) A The method according to Claim 14, ~~characterized in that~~ wherein at least 10% by weight of the filler of the fibrous web consists of the granulated filler, whereby its tensile strength is at least 10% better than that of a corresponding fibrous web that contains a mineral pigment that is essentially fully ground.

16. (Withdrawn, Currently Amended) A The method according to Claim 14, ~~characterized in that~~ wherein a granulated filler is used, the particle size (ϕ) of which is 1 to 100 μm , ~~preferably 5 to 50 μm .~~

17. (Withdrawn, Currently Amended) A The method according to Claim 14, ~~characterized in that~~ wherein the amount of granulated filler used is 3 to 60% of the web's dry weight.

18. (Withdrawn, Currently Amended) A The method according to Claim 14, ~~characterized in that~~ wherein the fibrous web containing the filler is coated with a coating composition.

19. (Withdrawn, Currently Amended) A The method according to Claim 14, ~~characterized in that~~ wherein to obtain a predefined level of opacity, the amount of coating pigment used is 30% smaller

than when providing a corresponding level of opacity with a fibrous web that contains powdery mineral pigments.

20. (Withdrawn, Currently Amended) A The method according to Claim 14, ~~characterized in that~~ wherein the substance in the granular form is plastically deformable under the effect of pressure and/or temperature.

21. (Withdrawn, Currently Amended) A method for improving the fire resistance properties of a fibrous web that contains a filler and has a good tensile strength, whereby the filler is a massive substance in a granular form, having a rotationally symmetrical shape and an inner part and a crust part, and the density of the inner part is lower than the crust part, ~~characterized in that~~ wherein the density of the inner part is about 10 to 90% of that of the crust part, and the amount of filler used is 3 to 60% of the amount of dry matter.

22. (Withdrawn, Currently Amended) A The method according to Claim 21, ~~characterized in that~~ wherein the substance in the granular form forms at least 10% by weight of the filler of the fibrous web.

23. (Withdrawn, Currently Amended) A The method according to Claim 21, ~~characterized in that~~ wherein the substance in the granular form forms 50 to 100% of the filler of the fibrous web.

24. (Withdrawn, Currently Amended) A The method according to Claim 21, ~~characterized in that~~ wherein the substance in the granular form is plastically deformable under the effect of pressure and/or temperature.

25. (New) The fibrous web according to Claim 1, wherein the amount of filler used is 30% to 60% of the amount of solids.